

TEMAFAST

General data

Standard sheet size:

- 1,5 x 1,5 m
- 1,5 x 1,0 m
- 1,5 x 3,0 m

Another sheet sizes are available upon the customer request.

Size tolerance: $\pm 2 \%$

Standard thickness:

- 0,4 – 6,4 mm
- with wire insertion:
- 0,8 – 6,4 mm

Thickness tolerance:

- 0,4 – 0,8 $\pm 0,1$ mm
- 1,0 – 6,4 $\pm 10 \%$

Surface:

All jointings are produced with an antistick surface on one side.

Wire insertion:

Majority of the styles can be supplied with a wire insertion.

Technical data

Marking acc. to	DIN 28 091-2	FA-MZ-1-0	
Marking acc. to	ASTM F 104	F712 120 M4	
Max. temperature	peak	°C	210
	continual	°C	140
Max. pressure	Bar		40

Typical parameters of 2 mm thick jointing

Density	DIN 28090-2	g/cm ³	1,6 - 1,9
Compressibility	ASTM F 36J	%	18
Recovery min.	ASTM F 36J	%	50
Residual stress (16h/175°C)	DIN 52 913	≈ MPa	20
Gas leakage $\lambda_{2,0}$	DIN 3535-6	≈ mg/(m.s)	0,1
Fluid resistance - thickness increase			
Oil IRM 903 (5h/150°C)	ASTM F 146	%	5
ASTM Fuel B (5h/23°C)	ASTM F 146	%	10


- 1 – suitable area (even for steam application)
- 2 – suitable extended area, technical advice is recommended
- 3 – for this area technical consultation is mandatory

Note: Maximum temperature and pressure values can not be used simultaneously.

TEMAFAST



Colour	Red
Description	Basic jointing manufactured from organic fibres with NBR binder.
Application	The jointing has a wide field of applications in all industrial branches at lower parameters.
Chemical resistance chart	available upon request.
Certification	DNV-GL, GOST
Updated information can be found on our websites.	



Chemical resistance table

	Temafast Economy	Temafast	Temafast special	Temaflex	Temasil	Temasil NG	Temasil HT	Temaplus	Temacarb	Grafem Economy	Temacid	Temac Auto	Temasil Titan
Acetic acid 100%	B	B	B	B	A	A	A	A	A	A	A	B	A
Acetone	C	B	B	B	B	B	B	B	B	B	A	B	A
Acetylene	A	A	A	A	A	A	A	A	A	A	A	A	A
Air	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluminium chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonia	B	B	B	B	B	B	B	B	B	B	B	B	A
Ammonium hydrogenphosphate	B	B	A	A	A	A	A	A	A	A	A	B	A
Barium chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Benzene	C	C	B	B	A	A	A	A	A	A	A	C	A
Boric acid	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A
Carbon dioxide	A	A	A	A	A	A	A	A	A	A	A	A	A
Copper sulphate	A	A	A	A	A	A	A	A	A	A	A	A	A
Crude oil	C	C	C	C	A	A	A	A	A	A	A	C	A
Cyclohexanol	A	A	A	A	A	A	A	A	A	A	A	A	A
Cyklohexanon	C	C	C	C	C	C	C	C	C	C	C	C	A
Di-butyl phthalate	C	C	C	C	B	B	B	B	B	B	B	C	A
Ethyl ether	B	B	B	B	A	A	A	A	A	A	B	B	A
Ethylen	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethylene glycol	A	A	A	A	A	A	A	A	A	A	A	A	A
Formic acid 10%	B	B	B	B	A	A	A	A	A	A	A	B	A
Glycerine	A	A	A	A	A	A	A	A	A	A	A	A	A
Hydraulic oil(mineral)	B	B	B	B	A	A	A	A	A	A	A	B	A
Hydrogen chloride dry	C	C	C	C	B	B	B	B	B	B	B	C	A
Hydrochlorid acid 20%	C	C	C	C	C	C	C	C	C	C	C	C	B
Chlorine dry	C	C	C	C	B	B	B	A	A	A	B	C	A
Chloroform	C	C	C	C	B	B	B	B	B	B	B	C	B
Iso-Octane	B	B	B	B	A	A	A	A	A	A	A	B	A
Kerosene	C	C	C	C	A	A	A	A	A	A	A	C	A
Methylene chloride	C	C	C	C	C	C	C	C	C	C	C	C	C
Natural gas	A	A	A	A	A	A	A	A	A	A	A	A	A
Nitric acid 20%	C	C	C	C	C	C	C	C	C	C	B	C	C
Nitrogen	A	A	A	A	A	A	A	A	A	A	A	A	A
Petrol	C	C	C	C	A	A	A	A	A	A	A	C	A
Petroleum	C	C	C	C	A	A	A	A	A	A	A	C	A
Phenol	C	C	C	C	C	C	C	C	C	C	B	C	C
Potable water	A	A	A	A	A	A	A	A	A	A	A	A	A
Potassium cyanide	B	B	A	A	A	A	A	A	A	A	A	B	A
Potassium iodide	A	A	A	A	A	A	A	A	A	A	A	A	A
Saturated steam	C	C	B	B	B	B	A	A	A	A	B	C	A
Silicon oil	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium hydrogen carbonate	A	A	A	A	A	A	A	A	A	A	A	B	A
Sodium hydrogen sulphite	B	B	A	A	A	A	A	A	A	A	A	A	A
Sodium hydroxide 25 %	C	B	B	B	B	B	B	B	B	B	A	C	B
Sodium chloride	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium sulphate	B	B	A	A	A	A	A	A	A	A	A	B	A
Sugar	A	A	A	A	A	A	A	A	A	A	A	A	A
Sulphuric acid 65%	C	C	C	C	C	C	C	C	C	C	B	C	B
Tartaric acid	A	A	A	A	A	A	A	A	A	A	A	A	A
Tetrachlormethane	C	C	B	B	B	B	B	B	B	B	B	C	B
Toluene	C	C	B	B	B	B	B	B	B	B	B	C	A
Transformer oil	B	B	A	A	A	A	A	A	A	A	A	B	A
Turpentine	C	C	B	B	A	A	A	A	A	A	A	C	A
Xylene	C	C	B	B	A	A	A	A	A	A	A	A	A

A-recommended

B-suitability depends on conditions

C-not suitable

If another medium is applied please contact our technical department.