



TECHNICAL DATA SHEET

Neopren Rubber Sheeting

Basic Properties	Value	Test Method	Unit
Base Polymer Type	SBR/CR	-	-
Indentation Hardness	60 Shore A - 4 + 5	ASTM D2240 00	Degrees
Specific Gravity	1.5 ± 0.05	ASTM D792	g/cm ³
Tensile Strength - Minimum	3	ASTM D412	Mpa
Elongation @ Break - Minimum	250	ASTM D412	%
Minimum Continuous Working Temperature	-20	-	° C
Maximum Continuous Working Temperature	70	-	° C
Maximum Intermittent Working Temperature	90	-	° C
Compression Set 70 Degrees 22 Hours	35 Max	ASTM D395 Method B	%
Insertion Type	On order / On stock		
Guidelines for Use			
Food Use Suitability	Not Recommended		
Abrasion Resistance	Moderate		
Ozone Weather Resistance	Moderate		
Flame Retardancy	Moderate		
Electric Resistance	Not Recommended		
General Purpose	Good		

All recommendations and information contained on this data sheet are, to the best of our knowledge, correct. Product specifications are intended as guidelines. Since conditions of service are beyond our control, users must satisfy themselves that products are suitable for the intended use. No guarantee or warranty is given or implied in respect of information or recommendations, or that any use of products will not infringe rights belonging to other parties. We reserve the right to change product design and properties without notification.